

DEXRON® FZG Scuffing – CEC L-84-02 (A10/16.6R/90C)
Report Forms
Form 1

Formulation Code							
Formulation Code							
SPONID	SponsorCode	Modification	Blend	Count	TestType	Lab	Test Gear Box

Blended Sample Testing Information ^A			
Candidate Percentage		Other Percentage	
Other Fluid ID			

^A If not a Blended Sample then report 100% Candidate Percentage, 0% Other Percentage, and “None” for Blend Fluid ID.

Test Identification			
Sponsor			
Sponsor In-House Number			
Lab In-House Number			
Alternate Code			
Test Number ^B			
Test Gear Box		Run Number	
Start Date		Start Time	
EOT Date		EOT Time	

^B Test Number = Test Gear Box – Run Number

Test Validity Statement	
This test has been conducted in a valid manner – YES or NO	
Test Laboratory	
Signature	
Typed Name	
Title	

DEXRON® FZG Scuffing – CEC L-84-02 (A10/16.6R/90C)

Pass/Fail Result

Form 2

Formulation Code	
Test Number	

Pass/Fail Result	
Failure Load Stage	

Test Conditions		
Motor Speed (reverse) - rpm		
Initial Fluid Temperature - °C		
Pitch Line Velocity - m/s		
Duration per Load Stage	Cycles	
	Time - min	

Weight Loss			
	Pre-Test - g	Post-Test - g	Total Loss - mg
Pinion			
Driver Gear			
Total Weight Loss - mg			

Damage Summary – Failure Load Stage	
Pinion Tooth	Damage Area - mm
1	
2	
3	
4	
5	
6	
7	
8	
9	
10	
11	
12	
13	
14	
15	
16	
Total Damage Area - mm	

Comments	